

2009 Trench Grab Sample Geochemical Results

Sample #	Copper <i>ppm</i>	Copper %	Lead <i>ppm</i>	Lead %	Zinc <i>ppm</i>	Zinc %	Silver <i>ppm</i>	Gold <i>ppb</i>	Cu/Pb/Zn %	Patterns of Mineralization by Abundance
TR08501								147		
TR08502	2070	0.21	2820	0.28	14900	1.49	29		1.98	Zn/Pb/Cu/Ag
TR08503	5870	0.59	2470	0.25	12200	1.22	36	317	2.06	Zn/Cu/Pb/Ag/Au
TR08504	15200	1.52	830	0.08	5530	0.55	38	199	2.15	Cu/Zn/Pb/Ag/Au
TR08505	2860	0.29	527	0.05	12700	1.27			1.61	Zn/Cu/Pb
TR08506	1310	0.13	771	0.08	14400	1.44			1.65	Zn/Cu/Pb
TR08507	3420	0.34			13300	1.33			1.67	Zn/Cu
TR08508	2910	0.29	1770	0.18	21600	2.16	17	179	2.63	Zn/Cu/Pb/Ag/Au
TR08509	1450	0.14	856	0.09						Cu/Pb

2009 Trench Grab Sample Geochemical Results (continued)

Sample #	Copper <i>ppm</i>	Copper %	Lead <i>ppm</i>	Lead %	Zinc <i>ppm</i>	Zinc %	Silver <i>ppm</i>	Gold <i>ppb</i>	Cu/Pb/Zn %	Patterns of Mineralization by Abundance
TR08510			565	0.06			16	155		Au/Zn
TR08511	1540	0.15	681	0.07	14300	1.43		317	1.65	Zn/Cu/PbAu
TR08512			825	0.08	2190	0.23		508		Au/Zn/Pb
TR08513	3100	0.31	927	0.09						Cu/Pb
TR08515	3980	0.39			1860	0.19	22	265		Cu/Au/Zn
TR08516			3350	0.33						Pb
TR08517			2190	0.22	4080	0.41	11			Zn/Pb/Ag
TR08518					2100	0.21				Zn
TR08519					2160	0.22				Zn
TR08520			2760	0.28	7050	0.71	11	206		Zn/Pb/Au
TR08521	12900	1.29	1170	0.12			20		1.41	Cu/Ag/Pb
TR08522			3140	0.31			14	191		Pb/Ag/Au
TR08523	7760	0.78	2290	0.23	1520	0.15	26		1.16	Cu/Pb/Zn/Ag
TR08524			4950	0.49	10700	1.69	22		2.18	Zn/Pb/Ag
TR08526	4390	0.44	1910	0.19	1220	0.12	28			Cu/Pb/Zn/Ag
TR08527					4780	0.48				Zn
TR08528			2700	0.27	1420	0.14				Pb/Zn
TR08529	1250	0.12	727	0.07	3630	0.36				Zn/Cu/Pb
TR08530	2140	0.21	5160	0.52	18700	1.87	27	228	2.61	Zn/Pb/Cu/Ag/Au
TR08531	1720	0.17	596	0.06	4100	0.41	10	285		Au/Zn//Cu/Pb/Ag
TR08532	16400	1.64	1340	0.13	6850	0.68	38	227	2.45	Cu/Zn/Pb/Ag/Au

TR08533	1280	0.13			1260	0.13				Cu/Zn
TR08534	3680	0.37	975	0.09	31500	3.15	16		3.63	Zn/Cu/Pb/Ag
TR08535					1600	0.16				Zn
TR08536	2950	0.29	1670	0.17	3520	0.35	13	219		Au/Zn/Cu/Pb/Ag
TR08537	2260	0.23	15900	1.59	9200	0.92	54		2.74	Pb/Zn/Cu/Ag
TR08538	11900	1.19	9421	0.94	4650	0.46	79	187	2.59	Cu/Pb/Zn/Ag/Au